

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

F-041

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
7 June 2001 (07.06.2001)

PCT

(10) International Publication Number  
WO 01/41233 A2(51) International Patent Classification<sup>7</sup>: H01M

(21) International Application Number: PCT/US00/42415

(22) International Filing Date:  
30 November 2000 (30.11.2000)


(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/168,761 6 December 1999 (06.12.1999) US  
09/723,353 27 November 2000 (27.11.2000) US(71) Applicant: AVX CORPORATION [US/US]; 801 17th  
Avenue South, Myrtle Beach, SC 29577 (US).(72) Inventors: MEITAV, Arie; 26 Dror Street, Rishon  
Le-Zion (IL). LANG, Joel; Palmach Street 30, 53406  
Givatayim (IL). FLEISCHER, Niles, A.; Hanasi Harishon  
Street 34, 76302 Rehovot (IL). LIFSCHITZ, David;Mishkanot Shaanancem, Hatikva Street 45, Jerusalem  
(IL). PECHERER, Eugene; Givati 14, Netanya (IL).  
CHODESH, Eli, Rosh; 1 Sigalit Street, Rishon Le-Zion  
(IL). MANASSEN, Joost; 57 Hanassi Harishon Street,  
76302 Rehovot (IL). RAWAL, Bharat; 1374 Links Road,  
Surfside Beach, SC 29575 (US).(74) Agent: MOOSE, Richard, M.; Dority & Manning, Attor-  
neys at Law, P.A., P.O. Box 1449, Greenville, SC 29602-  
1449 (US).(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,  
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,  
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,  
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,  
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,  
TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian

[Continued on next page]

(54) Title: ELECTROCHEMICAL ENERGY STORAGE DEVICE HAVING IMPROVED ENCLOSURE ARRANGEMENT

(57) Abstract: An improved electrochemical single or multi-  
cell energy storage device and casing are provided. The casing  
may be a pair of U-shaped shells, a single foil piece or even a  
tube-shaped structure which encases the internal electrochem-  
ical cell stack. The energy storage device and casing advanta-  
geously exhibit low internal resistance, low ESR, a high volt-  
age/capacity, and a low contact resistance between the internal  
stack and the outer casing.

WO 01/41233 A2



patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**Published:**

- *Without international search report and to be republished upon receipt of that report.*

**TITLE: ELECTROCHEMICAL ENERGY STORAGE DEVICE  
HAVING IMPROVED ENCLOSURE ARRANGEMENT**

**REFERENCE TO RELATED APPLICATIONS**

This application claims priority to Provisional Patent Application  
USSN 60/168,761, entitled "Novel Enclosures for Electrochemical  
Capacitors and Batteries" filed December 6, 1999, which is fully  
5 incorporated herein by reference.

**BACKGROUND OF THE INVENTION**

This invention generally relates to electrochemical systems for  
storage and release of electrical energy. In particular, the present invention  
relates to electrochemical systems for use in electronic circuits, for example,  
10 as capacitors or batteries. More particularly, the present invention relates to  
electrochemical systems for operation in electronic circuitry, for example, as  
capacitors or batteries, with either a non-liquid, organic solution, aqueous  
solution or a protonic medium electrolyte material positioned between the  
electrodes.

15 Further still, the present invention relates to improved designs for bi-  
polar assemblies that address the deficiencies in existing bi-polar designs. In  
particular, this invention relates to an assembly of a plurality of single cells  
of an electrochemical system.

20 As electronic devices and other electrical apparatuses become  
increasingly more portable and provide more functionality, advances must be  
made in the devices of such devices that enable such portability. As is often

the case with current electronics technology, the limiting factor in both size and functionality of an electronic apparatus is the size and weight of its component parts. In particular, the size and weight of its energy storage components. Additionally, the miniaturization of electronics has seen the  
5 push towards integrating various components into a single device to save both room and weight within both portable and stationary devices.

The current main energy source used for portable electronics is the electrochemical battery and/or the electrochemical capacitor. One of the limiting features of such current energy storage devices is the packaging of  
10 the electrochemical system. Prior art enclosures for flat and low height designs have suffered from several disadvantages. Coin cells for round shaped assemblies have needed to be crimped or swagged closed which requires expensive precision tooling. Further, such a method of enclosure requires accurate placement and/or control of closing pressures which can be  
15 very time consuming. Prismatic cell designs for rectangular and square shaped assemblies require precise corner radii and equivalent closing force across the entire area of the design to ensure good contact between the casing and the internal cells. While useful for their purpose, these prior art designs have forced higher production costs and longer production times due to the  
20 precision and technically complex assembly methods.

Further, in both coin and prismatic designs a grommet is needed to prevent shorting between the two poles of the electrochemical system. Should the electrochemical device consist of a plurality of cells in a stack then the grommet must serve to insulate the edge of the pack from the

enclosure and insulate the two portions of the enclosure that contact the two poles of the device. Thus the grommet acts to prevent the manufacture of some desirable forms of connections to a plurality of cells.

It is, therefore, desirable to provide a multi-cell energy storage device which may comprise either an electrochemical capacitor, a double-layer capacitor or a battery. In an electrochemical capacitor version of the present invention, which may also be referred to as a pseudo-capacitor or batcap, the electrodes comprise material that may participate in reversible charge transfer reactions. Thus, a portion of the energy is stored in the double-layer at the surface of the electrodes and another portion is contributed by the charge transfer reactions. In a double-layer capacitor version of the present invention, essentially all of the energy is stored in the double layer at the surface of the electrodes. In a battery version of the present invention, the anode and cathode materials are specifically chosen so that each reacts during operation of the cell. The chemical energy that is stored in the electrodes is converted to electrical energy via charge transfer reactions of active materials. It is also desirable to provide a new packaging for an electrochemical single or multi-cell energy storage device wherein the cells in a multi-cell design may be in series, parallel or a combination thereof by virtue of the device's construction in one integrated structure.

### **SUMMARY OF THE INVENTION**

The present invention recognizes and addresses various of the foregoing limitations and drawbacks, and others, concerning both the design of an electrochemical single or multi-cell energy storage device and methods

of packaging the same. Therefore, the present invention provides an improved electrochemical single or multi-cell energy storage device and outer packaging for the same.

It is, therefor, a principle object of the subject invention to provide an improved electrochemical single or multi-cell energy storage device. More particularly, it is an object of the present invention to provide an electrochemical single or multi-cell energy storage device within an improved casing. In such context, it is still a more particular object of the present invention to provide an electrochemical single or multi-cell energy storage device wherein the improved casing comprises a pre-formed metal sheet.

Still further, it is a principle object of this invention to provide an improved single layer, electrically conductive casing for an electrochemical single or multi-cell energy storage device. It is a further object of the present invention to provide such an improved electrochemical single or multi-cell energy storage device and casing which are simple and cost-effective to manufacture. In such context, it is an object of the present invention to provide a electrochemical single or multi-cell energy storage device and improved casing which exhibits a low equivalent series resistance (hereinafter ESR) and a low internal and contact resistance within the internal stack of the device and between the internal stack and the casing, respectively.

Additional objects and advantages of the invention are set forth in, or will be apparent to those of ordinary skill in the art from, the detailed

description as follows. Also, it should be further appreciated that modifications and variations to the specifically illustrated and discussed features and materials hereof may be practiced in various embodiments and uses of this invention without departing from the spirit and scope thereof, by virtue of present reference thereto. Such variations may include, but are not limited to, substitutions of the equivalent means, features, and materials for those shown or discussed, and the functional or positional reversal of various parts, features, or the like.

Still further, it is to be understood that different embodiments, as well as different presently preferred embodiments, of this invention, may include various combinations or configurations of presently disclosed features, elements, or their equivalents (including combinations of features or configurations thereof not expressly shown in the figures or stated in the detailed description).

These and other features, aspects and advantages of the present invention will become better understood with reference to the following description and appended claims. The accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate an embodiment of the invention and, together with the description, serve to explain the principles of the invention.

In one exemplary embodiment, there may be provided a multi-cell capacitor which comprises a carbon/plastic composite film coated with a metallic film on its external side as a terminal current collector, a plurality of non-conductive pre-formed isolating frames and within the openings formed



in each of the perforated isolating frames is present a high surface area carbon-based electrode to form capacitive electrode plates.

A bi-polar current collector, for use internal to a stack of series bi-polar connected cells, may comprise a single conductive polymer current collector. The polymer current collector within the bi-polar assembly need not have a metal film coating. On each side of the bi-polar current collector in the recesses formed within the perforated isolating frames may be placed a high surface area carbon-based electrode paste to form electrode plates.

The capacitor device may be formed by stacking successive layers of a bi-polar current collector and electrodes, the electrodes being separated by proton conductive polymer membranes. The ends of the stacks are terminated with a terminal current collector. The membranes function as a proton conductive layer within each capacitor cell. The stack may be potted, along its periphery only, with an insulating material, such as but not limited to an epoxy, in order to maintain a good seal and prevent ingress of moisture from the ambient environment. An outer conductive casing, such as a pre-formed metal sheet, serves as a shell around the periphery potting material and is in physical contact with the terminal current collectors.

In such a multi-cell electrochemical energy storage device, closure may be made without the use of a grommet and there exists no need for crimping or swagging. The internal cells may be connected in a bi-polar design in series in order to increase the pack voltage. Alternatively, a tongue design may be used to combine two or more bi-polar stacks in parallel within a single casing in order to increase capacity and decrease internal resistance.

The outer casing serves as a common pole for each of the stacks and the tongue as a common pole of the opposite polarity.

The casing may be a pair of U-shaped shells fitted over the epoxy-held internal stack or stacks and bonded along the adjoining sides of the shells. In an alternative exemplary embodiment, the casing may be a single sheet of pre-formed metal sheet bent approximate its midpoint to encase the epoxy-held internal stack and bonded along the adjoining ends of the foil sheet. In yet another exemplary embodiment, the casing may be a tube-shape. In any exemplary embodiment, the outer casing may be bent to form a pre-loaded structure that applies a spring-like loading to the shell in order to improve the contact between the shell and the stack and to offset thermal expansion cycles.

#### **BRIEF DESCRIPTION OF THE DRAWINGS**

A full and enabling disclosure of the present invention, including the best mode thereof, directed to one of ordinary skill in the art, is set forth in the specification, which makes reference to the appended figures, in which:

FIG. 1 is an exploded isometric view of the formation of the electrode plate in a perforated isolating frame with an affixed terminal current collector;

FIG. 2 is an exploded isometric view of one exemplary embodiment of a stack made in accordance with the present invention;

FIG. 3A is a cross-sectional view of an exemplary embodiment of a series connection among the cells of the internal stack in accord with the present invention;

FIG. 3B is a cross-sectional view of the exemplary embodiment of FIG. 2 showing a parallel connection of two bi-polar internal stacks with tongue in accord with the present invention;

5 FIG. 4A is an isometric view of one exemplary embodiment of an outer casing comprising two pre-loaded U-shaped shells in accord with the present invention;

FIG. 4B is an isometric view of the outer casing of the exemplary embodiment in FIG. 4A after final assembly of the device;

10 FIG. 5A is an isometric view of an alternative exemplary embodiment of an outer casing comprising a single sheet in accord with the present invention;

FIG. 5B is an isometric view of the outer casing of the exemplary embodiment in FIG. 5A after final assembly of the device;

15 FIG. 6 is an isometric view of an alternative exemplary embodiment of an outer casing comprising a tube in accord with the present invention and after final assembly of the device;

FIG. 7 is a table comparing conventional capacitor technology performance characteristics against those of a device made in accord with the present invention; and

20 FIG. 8 is a table comparing performance characteristics of various electrochemical devices made in accord with the present invention.

Repeat use of reference characters throughout the present specification and appended drawings is intended to represent the same or analogous features or elements of the invention.

**DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS**

Reference will now be made in detail to presently preferred  
embodiments of the invention, examples of which are fully represented in the  
accompanying drawings. Such examples are provided by way of an  
5 explanation of the invention, not limitation thereof. In fact, it will be  
apparent to those skilled in the art that various modifications and variations  
can be made in the present invention, without departing from the spirit and  
scope thereof. For instance, features illustrated or described as part of one  
embodiment can be used on another embodiment to yield a still further  
10 embodiment. Still further, variations in selection of materials and/or  
characteristics may be practiced, to satisfy particular desired user criteria.  
Thus, it is intended that the present invention cover such modifications and  
variations as come within the scope of the present features and their  
equivalents.

15 As disclosed above, the present invention is particularly concerned  
with an improved electrochemical single or multi-cell energy storage device  
wherein the cells are in series or parallel by virtue of the device's  
construction and an improved packaging therefor. The present invention is  
applicable to the generation of double-layer capacitors, pseudo-capacitors,  
20 and/or batteries, as well as, combinations thereof fabricated together or  
individually in a given assembly. For the sake of brevity, commonly-owned  
and assigned application entitled "ULTRA-THIN ELECTROCHEMICAL  
ENERGY STORAGE DEVICES", filed on November 22, 2000, and

claiming priority to a common provisional application is hereby incorporated fully by reference for all purposes.

In accord with the present invention, it is possible to fabricate such an electrochemical system with a low internal resistance by placing individual cells or bi-polar stacks in a common perforated isolating frame and connecting them with a series connection current collector that is not bi-polar. Within the system, the present invention provides greater versatility in achieving inter-cell or inter-subassembly connections in series, parallel or a combination thereof. Further, such systems may advantageously demonstrate a high voltage/capacitance value while maintaining a correspondingly low ESR and internal resistance.

Figure 1 depicts a non-conductive perforated isolating frame 20. Such a frame 20 forms a cavity for the electrode. The frame 20 allows for a bi-polar stack or single cell subassemblies to be generated. The frame 20 may be generally rectangular or other shapes.

Additionally depicted in Figure 1 is a current collector 24. The outer casing of the present invention functions as the current collector / external terminal of the device. Due to the planar geometry of the present invention the bi-polar electrical connections between cells and subassemblies require very good transverse conductivity. Additionally, the electrical connections need to be pressure insensitive. Conductive polymers and polymer composites have good transverse conductivity but poor lateral conductivity.

In one preferred embodiment, therefor, the current collector consist of two layers. The first layer is a conductive carbon layer which is in contact

with the cell electrode. The second layer is a metal which is positioned between the first layer and the casing. A metal, metal alloy or metallic film displaying high conductivity and low contact resistance is preferred in order to increase the lateral conductivity of the current collector 24. Unfortunately, many metals that exhibit high lateral conductivity and low cost are not stable in the presence of the electrolytes commonly used in double-layer capacitors, pseudo-capacitors, and batteries. As a result, the preferred embodiment of the current collector 24 has a composite second layer comprising a conductive material which is stable when in proximity with such electrolytes and a metal or metallic film.

One exemplary such conductive material is a polymer film or a carbon/plastic composite film. The metal or metal alloy may be, but are not limited to, nickel, chromium, lead, tin, silver, titanium, brass, gold and/or copper. Either of the two materials of the preferred composite second layer may act as the base of the composite layer. The polymeric material may be deposited onto the metal base layer using, but not limited to, any of the following methods: screen printing, brush painting, propellant spraying/air brushing, or casting. Alternatively, the metal may be deposited onto the polymeric substrate base layer using, but not limited to, any of the following methods: vacuum deposition, flame spray coating, molten bath dipping, heat lamination, electroless deposition, electroplating, plasma deposition, sputtering, or propellant spray/air brushing in a carrier.

Alternatively, the current collector 24 may comprise any number of layers. The combination of layers and materials may be adjusted to achieve a

desired combination of features including stability, lateral conductivity, interfacial contact resistance with the electrode, pressure insensitivity, solderability, creep, passivation, contact resistance, and permeability to the electrolyte, as well as, achieving the desired performance characteristics of the overall energy storage device.

In openings 22 within the common perforated isolating frames 20 may be placed a high surface area carbon-based paste 26. Such a paste 26 may work to form electrode plates 28. As shown in Figure 1, showing one such assembly 100, placing such a paste 26 within the openings 22 of the perforated isolating frame 20 may result in the formation of electrode plates 28. The paste is preferably a combination of a carbon material mixed with an aqueous sulfuric acid. The sulfuric acid concentration may range from 1-8 molar and the carbon content of the electrode may range from 8 to 36 weight per cent. Preferably the electrode thickness ranges from 30 to 300 microns.

In one exemplary embodiment of the electrochemical energy storage device, the electrodes comprise a high surface area carbon and a protonic medium. The protonic medium may be a material such as, but not limited to, water, aqueous acid solutions, sulfonic acids, poly-sulfonic acids such as polyvinyl sulfonic acid, protonic acids, compounds with one or more alcoholic hydroxyl groups, compounds with one or more carboxylic acid groups, compounds with one or more of the following groups: sulfonimides,  $-\text{PO}_2\text{H}_2$ ,  $-\text{CH}_2\text{PO}_3\text{H}_2$ ,  $-\text{OSO}_3\text{H}$ ,  $-\text{OPO}_2\text{H}_2$ ,  $-\text{OPO}_3\text{H}_2$ ,  $-\text{OArSO}_3\text{H}$ , and combinations thereof.

In one exemplary preferred embodiment an electrochemical multi-celled capacitor may be formed, as shown in Figure 2, by utilizing two assemblies (as shown in Figure 1) and a bi-polar assembly 200 with their respective electrode plates 28 by stacking the assemblies 100, 200 and 100, and separating them with proton conductive polymer membranes 30. The membranes 30 function as a proton conductive layer between electrode plates 28. The multi-celled capacitor may then be connected to a current collector 24 as described above.

The entirety of the internal stack 32, as shown in Figure 3A and 3B, except for the side opposing the current collector 24 may then be potted or coated in a non-conductive material 34, including, but not limited to an epoxy material. The outer casing 36 may then be formed on both sides of the existing stack 32 and be placed in electrical connection with the non-epoxy coated side of the stack 32. (The method of preparing and forming the outer casing will be discussed in detail below.) Such a device can be seen in Figure 3A.

Figure 3B depicts a similar electrochemical device. In this alternative exemplary embodiment, there are two internal stacks 32 jointly connected to a current collector (a.k.a. a tongue) 24 in parallel. In this preferred embodiment, the internal stacks 32 (separated only by the current collector 24) may be coated only on their ends with the non-conductive epoxy 34. This leaves a point of connection for each stack 32 with the outer casing 36. Such a device enhances the capacity and reduces the ESR of the device.



The present invention is characterized by a bi-polar stack of a plurality of cells. The stack is potted with a sealing material, such as, but not limited to an epoxy, on its four peripheral edges. A pre-formed metal casing covers two opposing peripheral edges of the potted stack while maintaining good electrical contact with the terminal current collectors. The terminal collectors being located on the non-potted opposing faces of the stack. This provides the advantages of smaller volumes, more versatile electrical connections, ease of changing the size and number of cells in an assembly without expensive re-tooling, and the possibility to make hybrid systems of a battery or batteries and a capacitor or capacitors in one package.

The outer casing 36 of the present invention, regardless of shape or style, are pressed into continuous contact with the internal stack 32. Similarly, the preferable material for the outer casing 36 is a pre-formed metal sheet, including, but not limited to stainless steel. A pre-formed metal sheet is desirable to enhance the conductivity of the outer casing 36. Stainless steel is a preferred material due to its stability characteristics. Unfortunately, stainless steel generally has a layer of oxidation which needs to be removed. To aid in reducing such a stainless steel outer casing's resistance, once the oxidation layer has been removed from the surface of the casing 36, it is coated with a highly conductive material such as but not limited to gold, nickel, platinum, silver, lead, tin, or brass. The material may be attached in any of the known methods of coating a substrate with a metal including but not limited to sputtering or electro- or electroless plating.

When the internal stack 32 is housed in the outer casing 36 and such is pressed into contact with the internal stack 32 with sufficient force, the result is a flexible energy storage device which is small in size, easily adjusted to suit the thickness of the internal stack 32 and exhibits a low ESR, high capacity/voltage, and is extremely cost effective to manufacture. Additionally, such a flexible design allows for the use of the same pressure levels to generate differing size devices with identical performance characteristics.

Figures 4A and 4B depict one exemplary such outer casing 36 which comprises two U-shaped shells 38 and 40 before and after completion of the manufacture of the device. Each shell includes side portions 42 and 44 extending around the internal stack 32. The side portions 42 and 44 may be allowed to overlap along the side of the internal stack 32 so as to encase the same. The side portions 42 and 44 are then joined together along the overlap in order to complete the outer casing 36.

As shown in Figure 4A, the U-shaped shells 38 and 40 may be bowed slightly so as to incorporate a spring-like load into the shells. Once affixed around the internal stack 32, such a spring-like loading may allow the outer casing 36 to cope with thermal expansion cycling of the device during its operation.

Similarly, Figures 5A and 5B depict an alternative exemplary outer casing 36. In this exemplary embodiment, the outer casing 36 comprises a single sheet 48 of the pre-formed metal sheet with end portions 50 and 52. As in the previous embodiment, end portions 50 and 52 may be allowed to

overlap each other when fitted around the internal stack 32. The end portions 50 and 52 are then joined along the length of the overlap to complete the construction of the device. Also as before, the outer casing 36 may be bowed 46 in order to incorporate the spring-like loading to counter thermal expansion cycling.

As depicted in Figure 6, a third exemplary embodiment of the outer casing 36 may be comprised of a seamless pre-formed metal tube structure 45. Similar to the preceding two exemplary embodiments, the multi-shell casing and the single sheet casing, the seamless pre-formed metal tube structure 45 encase the internal stack 32 and may incorporate a spring loading to offset the effects of thermal expansion.

Figure 7 provides a table comparing various capacitors technologies with that made in accordance with the present invention and showing the variability of the physical characteristics and performance level of the present invention. Similarly, Figure 8 provides a table comparing physical and performance characteristics of various electrochemical devices made in accord with the present invention.

Although a preferred embodiment of the invention has been described using specific terms and devices, such description is for illustrative purposes only. The words used are words of description rather than of limitation. It is to be understood that changes and variations may be made by those of ordinary skill in the art without departing from the spirit or scope of the present invention, which is set forth in the following claims. In addition, it should be understood that aspects of various other embodiments may be

interchanged both in whole or in part. Therefore, the spirit and scope of the appended claims should not be limited to the description of the preferred version contained herein.

CLAIMS

What is claimed is:

1. An electrochemical energy storage device, comprising:  
a plurality of cells in series, said plurality of cells being electrically connected via a plurality of bi-polar current collectors and wherein said plurality of cells and said plurality of bi-polar current collectors are stacked  
5 to form an assembly; and  
a pre-formed metal sheet outer casing electrically connected to said assembly and serving as an external electrical contact.
2. An electrochemical energy storage device as in claim 1, wherein said plurality of cells comprise at least one of a double-layer capacitor, a pseudo-capacitor, a battery or a combination thereof.
3. An electrochemical energy storage device as in claim 1, wherein said pre-formed metal sheet outer casing comprises two shells, each shell including side portions opposing each other to form an open-ended outer covering for said assembly, and wherein said side portions overlap each other and are joined together.
4. An electrochemical energy storage device as in claim 3, wherein said shells are U-shaped and form a box-shaped outer casing.
5. An electrochemical energy storage device as in claim 3, wherein said outer casing is joined at each of said overlapping side portions by welding.
6. An electrochemical energy storage device as in claim 3, wherein said pre-formed metal sheet is stainless steel.

7. An electrochemical energy storage device as in claim 6, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

8. An electrochemical energy storage device as in claim 7, wherein said highly conductive metal is gold.

9. An electrochemical energy storage device as in claim 3, wherein said outer casing is partially bowed to impart a spring loading thereto.

10. An electrochemical energy storage device as in claim 2, wherein said pre-formed metal sheet outer casing is a single sheet folded at least once approximate its midpoint and at least once at each end to form side portions, and wherein said side portions oppose each other to form an open-ended  
5 outer covering for said assembly, and wherein said side portions overlap each other and are joined together.

11. An electrochemical energy storage device as in claim 10, wherein said outer casing is joined at each of said overlapping side portions by welding.

12. An electrochemical energy storage device as in claim 10, wherein said pre-formed metal sheet is stainless steel.

13. An electrochemical energy storage device as in claim 12, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

14. An electrochemical energy storage device as in claim 13, wherein said highly conductive metal is gold.

15. An electrochemical energy storage device as in claim 10, wherein said outer casing is partially bowed to impart a spring loading thereto.

16. An electrochemical energy storage device as in claim 2, wherein said pre-formed metal sheet outer casing is a tube.

17. An electrochemical energy storage device as in claim 16, wherein said pre-formed metal sheet is stainless steel.

18. An electrochemical energy storage device as in claim 17, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

19. An electrochemical energy storage device as in claim 18, wherein said highly conductive metal is gold.

20. An electrochemical energy storage device as in claim 16, wherein said outer casing is partially bowed to impart a spring loading thereto.

21. A method of forming an electrochemical energy storage device, comprising the steps of:

providing a plurality of cells in series, said plurality of cells being electrically connected via a plurality of bi-polar current collectors and

5 wherein said plurality of cells;

stacking said plurality of bi-polar current collector connected cells to form an assembly; and

providing a pre-formed metal sheet outer casing for said assembly and electrically connected to said assembly, and wherein said outer casing serves as an external electrical contact.

22. A method of forming an electrochemical energy storage device as in claim 21, wherein said plurality of cells comprise at least one of a double-layer capacitor, a pseudo-capacitor, a battery or a combination thereof.

23. A method of forming an electrochemical energy storage device as in claim 22, wherein said pre-formed metal sheet outer casing comprises two shells, each shell including side portions opposing each other to form an open-ended outer covering for said assembly, and wherein said side portions overlap each other and are joined together.

24. A method of forming an electrochemical energy storage device as in claim 23, wherein said shells are U-shaped and form a box-shaped outer casing.

25. A method of forming an electrochemical energy storage device as in claim 23, wherein said outer casing is joined at each of said overlapping side portions by welding.

26. A method of forming an electrochemical energy storage device as in claim 23, wherein said pre-formed metal sheet is stainless steel.

27. A method of forming an electrochemical energy storage device as in claim 26, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

28. A method of forming an electrochemical energy storage device as in claim 27, wherein said highly conductive metal is gold.

29. A method of forming an electrochemical energy storage device as in claim 23, wherein said outer casing is partially bowed to impart a spring loading thereto.



30. A method of forming an electrochemical energy storage device as in claim 21, wherein said pre-formed metal sheet outer casing is a single sheet folded at least once approximate its midpoint and at least once at each end to form side portions, and wherein said side portions oppose each other to form an open-ended outer covering for said assembly, and wherein said  
5 side portions overlap each other and are joined together.

31. A method of forming an electrochemical energy storage device as in claim 30, wherein said outer casing is joined at each of said overlapping side portions by welding.

32. A method of forming an electrochemical energy storage device as in claim 30, wherein said pre-formed metal sheet is stainless steel.

33. A method of forming an electrochemical energy storage device as in claim 32, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

34. A method of forming an electrochemical energy storage device as in claim 33, wherein said highly conductive metal is gold.

35. A method of forming an electrochemical energy storage device as in claim 30, wherein said outer casing is partially bowed to impart a spring loading thereto.

36. A method of forming an electrochemical energy storage device as in claim 22, wherein said pre-formed metal sheet outer casing is a tube.

37. A method of forming an electrochemical energy storage device as in claim 36, wherein said pre-formed metal sheet is stainless steel.

38. A method of forming an electrochemical energy storage device as in claim 37, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

39. A method of forming an electrochemical energy storage device as in claim 38, wherein said highly conductive metal is gold.

40. A method of forming an electrochemical energy storage device as in claim 36, wherein said outer casing is partially bowed to impart a spring loading thereto.

41. An electrochemical energy storage device, comprising:  
a capacitor and a battery in parallel, said capacitor and battery being electrically connected to a bi-polar current collector;  
a pre-formed metal sheet outer casing electrically connected to said capacitor and battery and serving as an external contact.

42. An electrochemical energy storage device as in claim 41, wherein said pre-formed metal sheet outer casing comprises two shells, each shell including side portions opposing each other to form an open-ended outer covering for said assembly, and wherein said side portions overlap each other and are joined together.

43. An electrochemical energy storage device as in claim 42, wherein said shells are U-shaped and form a box-shaped outer casing.

44. An electrochemical energy storage device as in claim 42, wherein said outer casing is joined at each of said overlapping side portions by welding.

45. An electrochemical energy storage device as in claim 42, wherein said pre-formed metal sheet is stainless steel.

46. An electrochemical energy storage device as in claim 45, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

47. An electrochemical energy storage device as in claim 46, wherein said highly conductive metal is gold.

48. An electrochemical energy storage device as in claim 42, wherein said outer casing is partially bowed to impart a spring loading thereto.

49. An electrochemical energy storage device as in claim 41, wherein said pre-formed metal sheet outer casing is a single sheet folded at least once approximate its midpoint and at least once at each end to form side portions, and wherein said side portions oppose each other to form an open-ended  
5 outer covering for said assembly, and wherein said side portions overlap each other and are joined together.

50. An electrochemical energy storage device as in claim 49, wherein said outer casing is joined at each of said overlapping side portions by welding.

51. An electrochemical energy storage device as in claim 49, wherein said pre-formed metal sheet is stainless steel.

52. An electrochemical energy storage device as in claim 51, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

53. An electrochemical energy storage device as in claim 52, wherein said highly conductive metal is gold.

54. An electrochemical energy storage device as in claim 49, wherein said outer casing is partially bowed to impart a spring loading thereto.

55. An electrochemical energy storage device as in claim 41, wherein said pre-formed metal sheet outer casing is a tube.

56. An electrochemical energy storage device as in claim 55, wherein said pre-formed metal sheet is stainless steel.

57. An electrochemical energy storage device as in claim 56, wherein said outer casing is cleaned of any oxidation products and coated with a highly conductive metal.

58. An electrochemical energy storage device as in claim 57, wherein said highly conductive metal is gold.

59. An electrochemical energy storage device as in claim 55, wherein said outer casing is partially bowed to impart a spring loading thereto.





FIG 1

FIG 2






FIG. 3A




FIG. 3B




FIG. 4A




FIG. 4B






FIG 5A




FIG 5B




FIG. 6

Capacitor Type	Cap. (mF)	Voltage (V)	Dimen. (mm)	ESR (mΩ)	CV/c.c. (mFV/c.c.)
<u>Tantalum</u>	0.47	6.3	6.0 x 7.0 x 3.5	100	20
	1.0	4.0	6.0 x 7.0 x 3.6	30	26
<u>Electrolytic Aluminum solid capacitor organic semi-conductive electrolyte</u>	1.5	4.0	φ10 x L20	15	3.2
	2.2	4.0	φ12.5 x L22	10	3.3
	2.2	6.3	φ16 x L25	15	2.8
	4.7	6.3	φ16 x L26	100	6
<u>Electrolytic Capacitor</u>	15	6.3	φ16 x L35.5	30	13
	22	6.3	φ18 x L41	20	13
	15	10	φ18 x L35.5	30	17
	330	10	φ76 x L114	10	6
<b>BestCap<sup>TM</sup></b>	250	8.0	52 x 50 x 4.4	50	150
	250	5.5	48 x 30 x 3.2	60	300
	500	5.5	48 x 30 x 5.6	30	350
	600	4.5	48 x 30 x 5.0	25	380
	700	3.5	48 x 30 x 4.5	20	400
	60	5.5	28 x 17 x 3.2	200	210
	120	5.5	28 x 17 x 5.5	100	250

FIG. 7

Feature \ Model #	5.5/48x30-1	5.5/48x30-2	4.5/48x30-2	3.5/48x30-2	5.5/28x17-1	5.5/28x17-2	3.5/28x17-1	3.5/28x17-2
Nominal								
Voltage (V)	5.5	5.5	4.5	3.5	5.5	5.5	3.5	3.5
Capacitance <sup>(1)</sup> (mF)	250	500	600	700	60	120	200	60
ESR <sup>(2)</sup> (mΩ)	60	30	25	20	200	100	70	100
L.C. <sup>(3)</sup> (μA)	<10	<20	<10	<10	<2	<4	<2	<2
Cycle-life <sup>(4)</sup> (#)	>10 <sup>7</sup>							
Dimensions (mm)								
L x W	48x30				28x17			
H	3.2	5.6	5.0	4.5	3.2	5.5	4.0	1.8
Temperature (°C)	-20°C --- +60°C							

FIG. 8